

TEST REPORT

Report No: MS180411019E

Page 1 of 3

Customer Information:

Customer..... : Leisure Pursuits

Address..... : 7 Wolseley Business Park, Wolseley Close, Plymouth, PL2 3BY UK

Report on the submitted sample said to be:

Sample name..... : EVA MAT

Sample model..... : 6060-25

Sample description..... : /

Sample No. : S180411029

Amount of Sample..... : 5pcs

Sample Received Date... : Apr.11.2018

Completion Date..... : Apr.16.2018

Test Information:

No.	Item	Test Result
1	Hardness, Shore A	See Appendix 2



Testing: Jerry Peng

Inspected: Qiang Lu

Approved: Jason Xu

Jason Xu (Report Approver)

Verification code: r5ylj

TEST REPORT

Report No: MS180411019E

Page 2 of 3

Appendix 1

Sample Photo:




Figure 1. The sample photo of S180411029

TEST REPORT

Report No: MS180411019E

Page 3 of 3

Appendix 2

Test Item: Hardness, Shore A**1. Environment Condition:**

Temperature: 22.3°C ; Relative humidity: 53%R.H;

2. Test Sample:

Sample No.	Sample name	Sample model	Sample photo	Sample Num.
S180411029	EVA MAT	6060-25	See Appendix 1	5pcs

3. Test Equipment:

Name	Model No.	Valid Date to
Shore hardness tester (LX-A)	LX-A	Nov.12.2018

4. Testing Standard:

GB/T 531.1-2008 Rubber, vulcanized or thermoplastic - Determination of indentation hardness –
Part 1: Duromer method (Shore hardness)

5. Test Condition:

Shore A, Reading time: 1s

6. Test Results:

Sample No.	Test Results (HA)	
S180411029	1	20
	2	22
	3	21
	4	21
	5	19
	Med.	21

*** End of Report ***

This report is considered invalidated without the Special Seal for Inspection of the meixin testing, This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested.